



# P·DRAIN

## Pet Turf Drainage

### Applications:

Dog Runs  
Kennels  
Synthetic Turf Yards  
Dog Parks  
Roof Top Pet Runs

### Product Description:

**P·DRAIN** consists of a polymeric sheet cusped under heat and pressure to form a high flow, high compressive strength dimpled drainage core. The core is available as an impermeable sheet or punched, based on application. Impermeable core works well on slabs/indoor surfaces as it protects urine from being absorbed by the concrete. Punched core allows liquids to flow through to ground surfaces below. **P·DRAIN** creates air void so urine can be washed down through turf to avoid it being held by the turf and cause odor. It also creates a channel to convey the urine and wash down water directly to drains.




### Synthetic Turf


### P·DRAIN



Base Flooring



Impermeable



Punched

### Physical Properties

Core		Roll	
Compressive Strength (ASTM D-1621)	15,000 psf 719 kNm <sup>2</sup>	Roll Weight	50,100 lbs.      22,44 kgs.
Thickness (ASTM D-1777)	.40 in. 1.016 cm.	Roll Width	4, *6.5, *8.5 ft.      1.22, 1.98, 2.45 meters
Flow (ASTM D-4716)	21 gpm/ft width	Roll Length	50 ft.      15.24 meters
Hydraulic gradient = 1	260 lpm/m width	<b>*Special orders for 6.5' &amp; 8.5' widths available upon request.</b>	

The information contained herein is believed by JDR Enterprises, Inc. to be accurate and is offered solely for the customer's consideration, investigation and verification. Determination of suitability for use is the responsibility of the user. JDR's Limitations, Limited Warranty, & Disclaimer along with Standard Terms & Conditions apply. See [www.j-drain.com](http://www.j-drain.com) for more info. Limitations: J·DRAIN is resistant to chemicals in normal soil environments. However, some reagents may affect the performance of J·DRAIN. A JDR representative should be contacted for further information to determine the suitability of use of J·DRAIN in unusual soil environments. J·DRAIN should be limited to its exposure to ultra-violet sunlight. J·DRAIN should be backfilled or covered within seven days of installation. Disclaimer: All information, drawings and specifications are based on the latest published information at the time of printing. JDR reserves the right to make changes due to manufacturing improvements and engineering at any time. All physical properties are minimum average roll values (MARV). Standard variations of 10% in mechanical properties and 15% in hydraulic properties are normal.